

REPORT DOCUMENTATION PAGEForm Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE Conference Proceeding		3. DATES COVERED 21-22 Aug 2003	
4. TITLE AND SUBTITLE Venturi Oxygen Stripping as a Ballast Water Treatment to Prevent Aquatic Invasions & Ship Corrosion				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 61153N	
6. AUTHOR(S) Marion Tamburri, Brenda J. Little, Gregory Ruiz and Peter McNulty				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Naval Research Laboratory Oceanography Division Stennis Space Center, MS 39529-5004				8. PERFORMING ORGANIZATION REPORT NUMBER NRL/PP/7303/03/0051	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 N. Quincy St. Arlington, VA 22217-5660				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT <p>One of the most influential mechanisms for the introduction of aquatic nuisance species is transport in ship ballast waters. Although several ballast tank treatments to prevent transport of aquatic organisms appear promising, all existing approaches will result in significant costs to the shipping industry. The implementation of ballast water treatment measures would be hastened by providing the shipping industry with economic incentives for doing so. Our previous work suggests that deoxygenation may be such a treatment with benefit for ship owners by reducing corrosion, while simultaneously limiting the number of aquatic organisms surviving transport in ballast tanks.</p> <p>Our current investigations are providing the critical information required to evaluate the efficacy and feasibility of deoxygenation as a ballast water treatment to prevent aquatic invasions and tank corrosion. These results will ultimately lead to a full-scale shipboard evaluation of deoxygenation as a cost-saving ballast water treatment.</p>					
15. SUBJECT TERMS venturi oxygen stripping, ballast water treatment, aquatic invasions					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			Brenda J. Little
Unclassified	Unclassified	Unclassified	SAR	15	19b. TELEPHONE NUMBER (include area code) 228-688-5494

PUBLICATION OR PRESENTATION RELEASE REQUEST

Pubkey: 3576

NRLINST 5600.2

1. REFERENCES AND ENCLOSURES	2. TYPE OF PUBLICATION OR PRESENTATION	3. ADMINISTRATIVE INFORMATION
Ref: (a) NRL Instruction 5600.2 (b) NRL Instruction 5510.40D	<input type="checkbox"/> Abstract only, published <input type="checkbox"/> Book <input type="checkbox"/> Conference Proceedings (refereed) <input type="checkbox"/> Invited speaker <input type="checkbox"/> Journal article (refereed) <input type="checkbox"/> Oral Presentation, published <input type="checkbox"/> Other, explain	<input type="checkbox"/> Abstract only, not published <input type="checkbox"/> Book chapter <input checked="" type="checkbox"/> Conference Proceedings (not refereed) <input type="checkbox"/> Multimedia report <input type="checkbox"/> Journal article (not refereed) <input type="checkbox"/> Oral Presentation, not published
Encl: (1) Two copies of subject paper (or abstract)		STRN <u>NRL/PP/7303-03-51</u> Route Sheet No. <u>7303/</u> Job Order No. <u>M132-03</u> Classification <u>X</u> U <u> </u> C <u> </u> Sponsor <u> </u> approval obtained <u>X</u> yes <u> </u> no

4. AUTHOR

Title of Paper or Presentation Venturi OXYgen Stripping as a Ballast Water treatment
~~Evaluation of Deoxygenation as a Ballast Water Treatment to Prevent Aquatic Invasions and Ship Corrosion~~ to Prevent Aquatic
 Author(s) Name(s) (First, MI, Last), Code, Affiliation if not NRL INVASIONS + ship corrosion
 Mario Tamburri, Brenda J. Little, Gregory Ruiz, Peter McNulty

It is intended to offer this paper to the Maritime Environmental Engineering Technical Symposium 2003
 (Name of Conference)

21-AUG - 22-AUG-2003, Arlington, VA, Unclassified
 (Date, Place and Classification of Conference)

and/or for publication in Maritime Environmental Engineering Technical Symp
 (Name and Classification of Publication)

(Name of Publisher)

After presentation or publication, pertinent publication/presentation data will be entered in the publications data base, in accordance with reference (a).

It is the opinion of the author that the subject paper (is) (is not X) classified, in accordance with reference (b).

This paper does not violate any disclosure of trade secrets or suggestions of outside individuals or concerns which have been communicated to the Laboratory in confidence. This paper (does) (does not X) contain any militarily critical technology.

This subject paper (has) (has never X) been incorporated in an official NRL Report

Brenda J. Little, 7330

Name and Code (Principal Author)

Brenda J. Little
 (Signature)

5. ROUTING/APPROVAL			
CODE	SIGNATURE	DATE	COMMENTS
Author(s) Little	<u>Brenda J. Little</u>	<u>2/12/03</u>	
Section Head N/A			
Branch Head N/A			
Division Head Rhodes, acting	<u>Stat C Rhodes (Acting)</u>	<u>2/12/03</u>	1. Release of this paper is approved. 2. To the best knowledge of this Division, the subject matter of this paper (has <u> </u>) (has never <u>X</u>) been classified.
Security, Code 7030.1	<u>[Signature]</u>	<u>2/19/03</u>	1. Paper or abstract was released. 2. A copy is filed in this office <u>SSC-078-3</u>
Office of Counsel, Code 1008.3	<u>[Signature]</u>	<u>2/24/03</u>	
ADOR/Director NCST E.O. Hartwig, 7000	<u>[Signature]</u>		
Public Affairs (Unclassified/ Inlimited Only), Code 7030.4	<u>Brecky Roberts</u>	<u>2/19/03</u>	
Division, Code			
Author, Code			

☒ A - Approved for public release, distribution is unlimited.

☐ B - Distribution authorized to U.S. Government agencies only (check reason below):

- ☐ Foreign Government Information ☐ Contractor Performance Evaluation
☐ Proprietary Information ☐ Administrative/Operational Use
☐ Test and Evaluation ☐ Software Documentation

☐ Critical Technology

☐ Premature Dissemination

☐ Cite "Specific Authority" _____
 (Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
 (Insert Controlling DOD Office*)

☐ C - Distribution authorized to U.S. Government agencies and their contractors (check reason below):

- ☐ Foreign Government Information ☐ Software Documentation
☐ Administrative/Operational Use ☐ Critical Technology

☐ Cite "Specific Authority" _____
 (Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
 (Insert Controlling DOD Office*)

☐ D - Distribution authorized to DOD and DOD contractors only (check reason below):

- ☐ Foreign Government Information ☐ Critical Technology
☐ Software Documentation ☐ Cite "Specific Authority" _____
☐ Administrative/Operational Use

(Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
 (Insert Controlling DOD Office*)

☐ E - Distribution authorized to DOD components only (check reason below):

- ☐ Proprietary Information ☐ Premature Dissemination
☐ Foreign Government Information ☐ Software Documentation
☐ Administrative/Operational Use ☐ Contractor Performance Evaluation

☐ Critical Technology

☐ Direct Military Support

☐ Test and Evaluation

☐ Cite "Specific Authority" _____
 (Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
 (Insert Controlling DOD Office*)

☐ F - Further dissemination only as directed by _____
 (Insert Controlling DOD Office*)

Date statement applied _____ or higher DOD authority _____

☐ G - Distribution authorized to U.S. Government agencies and private individuals or enterprises eligible to obtain export-controlled technical data in accordance with regulations implementing 10 U.S.C. 140c.

Date statement applied _____

Other requests for this document shall be referred to _____
 (Insert Controlling DOD Office*)

*For NRL publications, this is usually the Commanding Officer, Naval Research Laboratory, Washington, DC 20375-5320

7. OTHER LIMITATION

☐ Classification

☐ NOFORN

☐ DTIC exempt (explain) _____

Classification Review
 (Initial/Date)

Substantive changes made in this document after approval by Classification Review and Public Release invalidate these reviews. Therefore, if any substantive changes are made by the author, Technical Information, or anyone else, the document must be returned for another Classification Review and Publication Release.

8. INSTRUCTIONS

Author completes and submits this form with the manuscript via line channels to the division head for review and approval according to the routing in Section 4.

1. NRL Reports.....Submit the diskette (if available), manuscript, typed double-spaced, complete with tables, illustrations, references, draft SF 298, and proposed distribution list.
2. NRL Memorandum Reports.....Submit a copy of the original, typed manuscript complete with tables, illustrations, references, draft SF 298, and proposed distribution list.
3. NRL Publications or other books, brochures, pamphlets, proceedings, or any other printed publications.....Handled on a per case basis by Site Technical Information Office.

Dr. Mario N. Tamburri, Dr. Brenda J. Little, Dr. Gregory M. Ruiz, and Peter D. McNulty

Venturi Oxygen Stripping™ as a Ballast Water Treatment to Prevent Aquatic Invasions and Ship Corrosion

ABSTRACT

One of the most influential mechanisms for the introduction of aquatic nuisance species is transport in ship ballast waters. Although several ballast tank treatments to prevent transport of aquatic organisms appear promising, all existing approaches will result in significant costs to the shipping industry. The implementation of ballast water treatment measures would be hastened by providing the shipping industry with economic incentives for doing so. Our previous work suggests that deoxygenation may be such a treatment with benefit for ship owners by reducing corrosion, while simultaneously limiting the number of aquatic organisms surviving transport in ballast tanks.

Our current investigations are providing the critical information required to evaluate the efficacy and feasibility of deoxygenation as a ballast water treatment to prevent aquatic invasions and tank corrosion. Specifically, we are: (1) exploring a rapid, in-line oxygen stripping system developed by NEI Treatment Systems, Inc. to optimize the deoxygenation process, (2) examining the impact of this oxygen stripping technique on the immediate and long-term survival of natural Chesapeake Bay planktonic organisms, and (3) quantifying corrosion rates and establishing the mechanism under deoxygenated conditions (with particular emphasis on microbiologically influenced corrosion). These results will ultimately lead to a full-scale shipboard evaluation of deoxygenation as a cost-saving ballast water treatment.

STATEMENT OF PROBLEM

Invasions by non-native aquatic species are increasingly common worldwide in coastal habitats (Cohen and Carlton 1998). Estuaries in particular harbor large numbers of introduced

species (Ruiz et al. 1997; 2000a). For instance, there are 234 known invasive species in the San Francisco Bay and Delta (Cohen and Carlton 1998), 119 in the Hudson River Basin (Mills et al. 1996), and 99 in Port Phillip Bay (Australian Southern coast; Hewitt et al. 1999). Even in these relatively well-studied areas, there are many more invaders to be discovered because surveys for non-native species have focused on conspicuous, macroscopic taxa.

Although the effects of many of these introduced aquatic species on habitats and communities remain largely unknown, some of them have had demonstrably strong negative influences. Harmful effects resulting from aquatic invasions include: decrease in abundance and even local extinction of native species (e.g., by the Japanese mudsnail *Batillaria attramentaria* in California; Byers 1999), alteration of habitat structure (e.g., by the Atlantic cordgrass *Spartina alterniflora* on the Pacific coast; Daehler and Strong 1996), and massive economic costs due to biofouling (e.g., by the European zebra mussel *Dreissena polymorpha* in the Great Lakes; Johnson and Carlton 1996).

Global shipping, which moves 80% of the world's commodities and is fundamental to international trade, inadvertently transports many aquatic organisms (see review by National Research Council 1996). In particular, ballast water (water that is pumped into dedicated ballast tanks or into empty cargo holds to increase draft, change trim, regulate stability, or maintain stress loads) is considered the most important vector responsible for transporting and introducing non-native aquatic species to new biogeographic regions (Carlton and Geller 1993). Vessels commonly pump in water in one port, and discharge it at another. Many planktonic organisms captured in ballast waters survive even lengthy journeys onboard ships. Examination of ballast water upon arrival of

DISTRIBUTION STATEMENT A
Approved for Public Release
Distribution Unlimited

vessels has revealed living and viable bacteria (McCarthy and Khambaty 1994; Ruiz et al. 2000b), protists (Galil and Huelsmann 1997; Pierce et al. 1997), dinoflagellates (Hallegraeff and Bolch 1991), diatoms, zooplankton, benthic invertebrates, and fish (Williams et al. 1988; Carlton and Geller 1993; Wonham et al. 2000). Increasing international traffic by increasingly large vessels translates into ever more enormous amounts of water, and planktonic organisms, being moved around the world by ballast water transport (e.g., the largest oil tankers can now have up to 40,000,000 gallons of ballast water capacity). Although other vectors, such as ship-fouling and aquaculture, are still important mechanisms introducing aquatic species to new places, none match ballast water transport for the sheer magnitude of organisms moved around the world (National Research Council 1996).

Theoretical and empirical studies have shown that "propagule pressure" (the number of larvae, spores, seeds, or dispersive adults introduced) is one of the best predictors of invasion success (Williamson 1996). Therefore, areas adjacent to large international ports are particularly susceptible to invasions. For example, the Chesapeake Bay has been inoculated with non-native species for approximately four centuries. Today, the Chesapeake receives annually greater than three billion gallons of ballast water from foreign ports around the world (Smith et al. 1999). This quantity of foreign ballast water greatly exceeds that released at other Atlantic ports of North America and has been implicated in many of the over 150 documented non-native species now found in the Chesapeake Bay (Ruiz et al. unpublished data).

Since transport in ballast tanks is a key source of introduced propagules, attention has focused recently on means of limiting ballast water introductions (National Research Council 1996). It has proven challenging to find an environmentally friendly technique that is effective at reducing introductions and yet also acceptable to the shipping industry in terms of safety, time, and cost. For instance, the offshore exchange of ballast water is currently recommended to reduce introductions (since coastal organisms are unlikely to invade open ocean areas, and vice versa), but the process is

time-consuming, costly, cannot be performed in rough sea conditions, and has limited effectiveness in some environments and for certain vessel designs (e.g., Cooper et al. 2002; Ruiz et al. unpublished data).

Analysis of different ballast water treatments by the National Research Council (1996) suggested that intensive filtration, thermal treatment, and biocides were the most promising options. However, discharging warm water or water laden with biocides potentially threatens biological communities around ports, biocides can be dangerous to crew members, and fine filtration systems are expensive to install and maintain (National Research Council 1996). Recently, additional treatment options have been proposed such as ultraviolet radiation, centrifugation, and ozonation. However, unless mandated to do so by law, the shipping industry is unlikely to voluntarily implement any costly, time-consuming, or potentially dangerous procedures.

The implementation of ballast water treatment measures would be hastened by providing the shipping industry with economic incentives for doing so. Our previous work suggests that deoxygenation may be such a treatment with benefit for ship owners through corrosion prevention, while simultaneously limiting the number of aquatic organisms surviving transport in ballast tanks.

Corrosion of ballast tanks from exposure to seawater is commonly destructive and costly for individual vessels and the shipping industry as a whole. Currently painting and sacrificial anodes are used almost exclusively as the means to prevent ballast tank corrosion, but it is expensive and time-consuming. Investigators from Sumitomo Heavy Industries, Ltd. of Japan have therefore proposed an alternative corrosion prevention technique that purges oxygen from ballast tanks with nitrogen gas (Matsuda et al. 1999). This new anticorrosion technology was derived from the basic concept that removing oxygen from the ballast tanks will limit the oxidation of metallic structures and thus greatly reduce the problems associated with corrosion. Our initial proof-of-principle and laboratory studies on the effectiveness of deoxygenation to

prevent the transport on non-native species and the full-scale, field study on ballast tank corrosion demonstrated that this approach may both save the shipping industry money on corrosion prevention while removing a large proportion of the organisms typically found in ballast waters (Tamburri et al. 2002; summarized below).

The primary objective of our current work is to test the efficacy of deoxygenation in removing ballast water organisms while reducing ballast tank corrosion, using a series of experiments in the laboratory and in dock-side mesocosms (i.e., 25 gallon cylindrical tanks). Although the effects of low oxygen or hypoxia (< 1.0 mg/l oxygen) on aquatic organisms (see reviews by Grieshaber et al. 1994, Diaz and Rosenberg 1995; Tamburri et al. 2002) and corrosion (e.g., Hardy and Bown 1984; Lee et al. 1993a) are well documented, our current work is the first large-scale, direct investigation of both simultaneously. Furthermore, by conducting the experiments across different scales, we are collecting the critical data required to evaluate the feasibility of deoxygenation as a ballast water treatment.

BACKGROUND AND PREVIOUS WORK

Deoxygenation to Stop Invasions – The objectives of our previous work were to evaluate if deoxygenation used to reduce ballast tank corrosion could also successfully curb the introduction of aquatic organisms. Our publication in *Biological Conservation* (Tamburri et al. 2002) presents a synthesis and reanalysis of the relevant parts of the Japanese technical report describing an 18-month shipboard field study implementing this anticorrosion approach (Matsuda et al. 1999). In summary, Sumitomo Heavy Industries found that deoxygenating ballast waters (purging with nitrogen gas to drop oxygen levels to approximately 0.2 mg/l) decreases the rate of uniform corrosion to 10% of untreated ballast tanks and represents a significant saving for ship owners when compared to other corrosion prevention approaches currently available (approximately \$80,000/year/vessel saved when

compared to the standard painting and maintenance). These results are supported by the anecdotal observations of the Hellestont Group, who state that corrosion in ballast tanks on their tankers has been “completely arrested” after the addition of anodes and low-sulphur inert gasses.

To test whether deoxygenation may also limit invasion, we carried out laboratory oxygen tolerance experiments on the larvae of three widely introduced aquatic nuisance species (Australian tubeworm *Ficopomatus enigmaticus*, European zebra mussel *Dreissena polymorpha*, and European green crab *Carcinus meanas*) using oxygen levels comparable to those in the shipboard corrosion study (< 0.8 mg/l). Significant levels of mortality were found in nitrogen treated water after only two or three days (Figure 1).




Figure 1. Mean percent survival (\pm SD) of *Ficopomatus enigmaticus* (polychaete), *Carcinus meanas* (green crab), and *Dreissena polymorpha* (zebra mussel) larvae after 2 or 3 days of being held in water open to air (normoxia) and in water where oxygen was removed by purging with nitrogen gas (hypoxia). From Tamburri et al. 2002.

Two separate literature reviews of oxygen tolerance for various aquatic species further support the conclusion that few organisms will be able to withstand extended periods (more than 48 hours) of exposure to deoxygenated ballast water (Table 1). For example, by far the most abundant animals overall found in ballast water are copepod crustaceans (Carlton and Geller 1993; Smith et al. 1999) and shallow water and estuarine species that are unable to withstand 24 hours of exposure to hypoxia (e.g.,

Roman et al., 1993; Lutz et al. 1994; Stalder and Marcus 1997).

Table 1. A representative sample of time until significant mortality (LD₅₀, LT₅₀, or survivorship in treatment significantly less than control) was found for aquatic organisms held under various low oxygen concentrations. From Tamburri et al. 2002.

Species	O ₂ level	Time to sign. mort.	Source
<i>Astronotus ocellatus</i> fish - adults	0.4 mg/l	24 hours	Muusze et al. 1998
<i>Ophiura albida</i> brittle star - adults	0.1 mg/l	60 hours	Vistisen and Vismann, 1997
<i>Gammarus pseudolimnaeus</i> amphiod - adults	1.5 mg/l	24 hours	Hoback and Barnhart, 1996
<i>Platichthys flesus</i> fish - juveniles	1.0 mg/l	2 hours	Tallqvist et al. 1999
<i>Loimia medusa</i> polychaete - adults	0.5 mg/l	72 hours	Llanso and Diaz, 1994
<i>Meganycitiphanes norvegica</i> krill - adults	1.8 mg/l	2 hours	van den Thillart et al. 1999
<i>Cancer irroratus</i> crab - larvae	1.7 mg/l	4 hours	Vargo and Sastry, 1977
<i>Crassostrea virginica</i> oyster - larvae	0.02 mg/l	18 hours	Widdows et al. 1989

Small plant and algal parts (fragments, spores, and seeds) as well as single-celled phytoplankton, protoctists, fungi, and bacteria are also often transported in ballast water. These microscopic components of ballast water have not been thoroughly characterized. However, it appears from our reviews that their tolerances for low oxygen environments will vary greatly.

There are examples of species that are very sensitive to hypoxic conditions (e.g., filamentous fungi, Padgett et al. 1989; zoospores of the seaweed *Undaria pinnatifida*, Mountfort et al. 1999), as well as counter-examples of species that can withstand low oxygen levels (e.g., resistant cysts of dinoflagellates, Hallegraeff 1998). Marine bacteria, in particular, will have dramatically different responses to the conditions created in nitrogen treated ballast tanks. While most obligate aerobic strains will be unable to grow over extended periods of hypoxia, some facultative and obligate anaerobic bacteria may actually thrive under the conditions found in treated ballast. We therefore conclude that ballast water deoxygenation (maintaining hypoxia) would likely be highly effective at reducing introductions of aquatic animals (larvae, juveniles, and adults stages) but may have mixed success at eliminating introductions by members of other taxa.

Although other ballast water treatment options might be more comprehensively effective, they come at greater environmental and financial cost. For example, biocides may be hazardous for the crew as well as for native organisms in the vicinity of the ballast discharge (National Research Council 1996). Moreover, these techniques come at a significant price for ship owners. Clearly, until required to do so, the shipping industry is unlikely to voluntarily install expensive ballast water treatment technologies. Indeed, Mountfort et al. (1999), who did not consider the anticorrosion benefits, concluded that deoxygenation of ballast water with nitrogen was reasonably effective at killing aquatic organisms but impractical for shipboard operations due to financial costs. In contrast, we propose that widespread voluntary adoption of deoxygenation may result if the economic benefits for controlling corrosion are demonstrated definitively and become well known. While ballast water treatments have been controversial, raising conflicts between environmentalists and ship owners, we feel deoxygenation represents a working solution that should appeal to both parties.

Ballast Tanks Corrosion – The vast majority of the world's fleet of ships, including military and

commercial vessels, are constructed of carbon steel. Steel corrodes quickly when exposed to oxygen and water. Ocean-going vessels are particularly susceptible to corrosion, due to the accelerated corrosion rate in exposure to salt water. Corroded steel structures on a vessel decrease seaworthiness so extensive measures are taken to prevent corrosion and, inevitably, in repair. The cost to prevent, maintain, and repair corrosion on individual vessels can run into the millions of dollars (e.g., \$5.5 million to replace 1400 tonnes of ballast tank steel on *Wind Conquest*, Marine Engineering Review 1991).

One area in a ship where corrosion is of particular concern is in the ballast tanks. Prolonged exposure of the ballast tank structure to water (often salt water) creates a condition conducive to rapid corrosion. The cost to paint ballast tanks is typically \$5.00 to \$10.00 per square meter with the cost to repair corroded areas at approximately \$500 per square meter (Fairplay 1993). With large cargo vessels and oil tankers having hundreds of thousands of square feet of ballast tank surface area, preventing and treating corrosion is extremely costly.

Therefore, any measure for controlling aquatic invasive species in ballast tanks cannot be evaluated without consideration of the impact on corrosion. For example, both chlorination (McCracken 2001) and ozonation (Andersen 2001) of seawater are known to exacerbate corrosion of steel. Clearly, removal or reduction of oxygen will eliminate or reduce direct oxidation reactions related to corrosion. However, deoxygenation could increase corrosion resulting from the activities of naturally occurring microaerophilic, facultative or obligate anaerobic bacteria. Acid-producing bacteria (APB) and sulfate-reducing bacteria (SRB) grow under anoxic conditions and produce corrosive metabolic by-products (organic acids and sulfides, respectively).

The corrosion rate of carbon steel is not influenced by pH over the range of 4.5 to 9.5 in distilled and tap waters (Boyer and Gall 1985). Over this range, corrosion products maintain a pH of 9.5 at the metal surface. Below pH 4.0, hydrogen evolution begins and corrosion

increases dramatically. Although it is extremely unlikely that APB will change the bulk pH of carbonate buffered seawater, APB can reduce pH locally under colonies and produce corrosion in carbon steel (Pope 1995).

All seawater contains 2 gm l⁻¹ sulfate than can be reduced to sulfide by SRB in the absence of oxygen. Reviews by Miller and Tiller (1970), Iverson (1974) and Postgate (1979) provide examples and details of microbiologically influenced corrosion of iron and mild steel under anaerobic conditions caused by SRB.

Microbiologically influenced corrosion failures have been reported for mild steel pipping and equipment exposed in the marine environment (Sanders and Hamilton, 1986; Eidsa and Risberg 1986; Eashwar et al. 1990) soil (King et al. 1983; Kasahara and Kajiyama 1986; Alanis et al. 1986; Pope et al. 1988; Dias and Bromel 1990), oil refining industry (Winters and Badelek 1987), fossil fuel and nuclear power plants (Soraco et al. 1988; Licina 1988, Pope 1986 and 1987; Bibb 1986) and process industries (Pacheco, 1987; Honneysett 1985; Tatnall et al. 1981). Deoxygenation can also result in putrefaction, anaerobic breakdown of sulfur-rich proteins, and levels of sulfides will not be limited to the sulfate concentration in the seawater. Sulfide reacts with iron oxide, formed in the atmosphere or in oxygenated seawater, to produce a non-tenacious iron sulfide layer that can be removed with stress or converted back to an oxide by the introduction of oxygen. In either case the sulfide layer is not uniformly removed or oxidized, creating adjacent anodic and cathodic regions and aggressive corrosion.

The most corrosive operating condition is one in which carbon steel is exposed to alternating oxygenated/deoxygenated conditions (Hardy and Bown 1984; Lee et al. 1993a; Lee et al. 1993b). Under constant oxygenation an oxide will form that provides corrosion resistance. Under anaerobic conditions a sulfide layer will form and corrosion rate will decrease until oxygen is introduced. The result of alternating operating conditions is severe pitting. Additionally, concentrations of sulfides can produce sulfide assisted stress corrosion cracking in carbon steel. Most reported cases of SRB induced corrosion of carbon steel in marine

waters are in environments with some dissolved oxygen in the bulk medium (Hamilton 1986). Anaerobic conditions and sulfides form within marine biofilms at biofilm/metal interfaces, independent of bulk oxygen concentrations. Exposure of iron sulfide corrosion products to oxygen creates differential aeration cells and localized corrosion. However, because aerobic microorganisms form biofilms, continuous deoxygenation to prevent biofilm production has been suggested as a way to reduce microbial induced corrosion (Lutey 200; Pope and Pope 2001).

CURRENT INVESTIGATIONS

The basic objective of our ongoing research is to quantify the effectiveness of deoxygenation in removing ballast water organisms while reducing ballast tank corrosion. Specifically we are: (1) exploring a rapid, in-line oxygen stripping system developed by NEI Treatment Systems, Inc. to optimize the deoxygenation process, (2) examining the impact of this oxygen stripping technique on the immediate and long-term survival of natural Chesapeake Bay planktonic organisms, and (3) quantifying corrosion rates and establishing the mechanism under deoxygenated conditions (with particular emphasis on microbiologically influenced corrosion).

Optimizing Deoxygenation – A key to the success of deoxygenation as a ballast water treatment is to design the most efficient method for maintaining levels of oxygen in tanks that both kills the majority of aquatic organisms while also reducing corrosion rates – below 1.0 mg/l. Evaluations of several approaches and a series of pilot studies have led to the conclusion that Venturi Oxygen Stripping represents the most effective and economical method of deoxygenation for use aboard vessels (NEI Treatment Systems, Inc., unpublished data).

The deoxygenation method proposed by Sumitomo Heavy Industries for ballast water treatment entails bubbling an inert gas into the ballast tanks after they have been filled. The shipboard trial by Matsuda and colleagues (1999) included vertical pipes installed into a ballast tank from which pure nitrogen gas was

pumped into the water for the “sparging” of oxygen. The tank was also sealed at the deck to permit nitrogen purging of the headspace. This method may achieve some deoxygenation through the contact of the nitrogen bubbles with the water, but primarily relies on diffusion of oxygen through the water surface in the tanks. Although hypoxic conditions were achieved, the sparging and purging of oxygen took days and relied on both the presence of a large headspace in the ballast tank filled with nitrogen gas (a free surface condition that is typically avoided since it can destabilize the vessel as water moves within tanks) and on large volumes of expensive inert gas. Although the basic principles are sound and experimental results significant, the method used by Sumitomo Heavy Industries for deoxygenation appears to be inefficient and relatively costly to employ (approximately \$3.5 million for installation on a vessel).

Other deoxygenation methods (e.g., vacuums, horizontally placed diffuser plates) use techniques with varying degrees of effectiveness. However, our investigations suggest that the most efficient way to remove oxygen from ballast water is through introducing microfine bubbles of an inert gas as water is being pumped into the tanks. The smaller a bubble, the higher the ratio of surface area to volume and thus the higher gas-to-water contact surface where transfer takes place. Therefore, we have begun work with NEI Treatment Systems, Inc. to optimize the deoxygenation of ballast water through Venturi Oxygen Stripping. Initial laboratory results show that the time until low-oxygen equilibrium conditions in the water are reached can be less than four seconds, the oxygen stripping system will require very few modifications for shipboard applications, and most importantly, it may be much more cost effective than the treatment system proposed by Sumitomo Heavy Industries described above.

Survivorship of natural planktonic organisms subjected to deoxygenated water – Dockside, mesocosm experiments are being conducted at the Chesapeake Biological Laboratory (CBL), University of Maryland Center for Environmental Science, in Solomons, Maryland (Figure 2).




Figure 2. Top, CBL research pier. Left, filling a treated tank. Right, dockside mesocosm experimental setup.

Natural seawater is pumped from one meter below the surface into 10 identical 20-gallon, airtight acrylic cylinders, held inside a laboratory at the end of the CBL pier. All water first passes through a 1 cm screen – the mesh size commonly used to restrict intake into ship ballast tanks. In five control cylinders, seawater is delivered directly from the pump. However, in five treated cylinders, the seawater first passes through the rapid, in-line oxygen stripping system. Physical conditions are monitored throughout the experiments with oxygen, temperature, and conductivity sensors sealed within the cylinders. Oxygen levels in the control cylinders are always above 8.0 mg/l whereas water in the treated cylinders enters and remains hypoxic (< 0.8 mg/l) throughout the experiments.

To examine mortality over time as a result of deoxygenation, one treated and one control cylinder are drained completely through a bottom valve 1, 24, 48, 72, and 96 hours after filling. The treated and control cylinder at each sampling period are then compared for

abundance and mortality of three separate planktonic community components.

- Zooplankton – the entire volume is sieved through a 50 μm screen and evaluated for total abundance and living versus dead individuals. The percentage of living individuals will be quantified by examining reactivity or movement under dissecting microscope.
- Phytoplankton – water passing through the 50 μm sieve are analyzed for chlorophyll a concentrations. Subsamples are examined under a compound microscope to identify major algae groups and cell abundance will be determined by flow cytometry.
- Bacteria – the density of bacterial cells are determined by flow cytometry and subsamples of the water are used to determine total plate counts of culturable bacteria.

Additionally, subsamples of abundant zooplankton (such as copepods) that are scored as dead after the 48-hour deoxygenation treatment are placed aerated natural seawater to determine their ability to recover and resume swimming after removal from hypoxic conditions.

This process is being repeated five times during the seasons when planktonic organisms are most abundant (April through September 2003) in the Chesapeake Bay.

Initial results suggest that in addition to hypoxia alone causing rapid mortality (greater than 99% of organisms 50 μm or larger killed in less than 48 hours), the physical/mechanical disturbances experienced as organisms pass through the Venturi injector will also kill some species. The treatment also appears to dramatically reduce the abundance of algae and importantly does not appear to increase the total numbers of bacteria.

Rates and mechanism of corrosion under deoxygenated conditions – Laboratory experiments are underway to answer the following questions:

- How does deoxygenation affect bulk water chemistry, biofilm formation and biofilm/metal interfacial chemistry?

- Does microbiologically influenced corrosion occur under deoxygenated conditions and if so by what mechanisms?
- What is the impact of O₂ on corrosion that has developed under deoxygenated conditions? Does the mechanism shift? Is the rate accelerated?

Corrosion experiments with control and deoxygenated natural seawater are being conducted at the Naval Research Laboratory (NRL), Corrosion Facility, in Key West, FL and at the NRL, Stennis Space Center, MS. Individual tanks are maintained with either oxygenated seawater (> 8.0 mg/l) or seawater that has passed through the rapid, in-line oxygen stripping system (0.8 mg/l oxygen) in a darkened anaerobic hood (Figure 3).




Figure 3. NRL corrosion experimental setup.

Samples are collected every two weeks over one year to assess changes in dissolved and particulate water chemistry (dissolved oxygen, dissolved organic carbon and nitrogen, particulate organic carbon and nitrogen, bulk pH, sulfide concentration) using standard techniques. Serial dilutions are used to determine most probable numbers of APB, SRB, general heterotrophic aerobes, and anaerobes (Bioindustrial technologies, Inc.). Carbon steel coupons are also exposed in each tank of oxygenated and deoxygenated natural seawater. Coupons have been orientated both horizontally and vertically to simulate tank bottoms and

sidewalls, respectively. Triplicate samples from both containers are removed every two weeks, fixed in glutaraldehyde and examined to assess the extent of biofilm formation and corrosion morphology. Environmental scanning electron microscopy (ESEM) and energy dispersive spectroscopy (EDS) is being used to characterize the corrosion morphology, biofilm structure and corrosion product composition on the metal surface. Swabs made of the coupon surface and serial dilutions used to determine the microbial composition of the biofilm. Finally microelectrodes are used to make O₂ profiles through the biofilms. Polarization resistance and open-circuit potential will be used to monitor electrochemistry and corrosion over time.

CONCLUSION

Our fundamental goal is to provide the science necessary for the development of effective ballast water management strategies and policies. Through rigorous laboratory and dockside/mesocosm experiments, our work will provide the information required to evaluate the efficacy and feasibility of deoxygenation as a ballast water treatment to prevent aquatic invasions and will be the basis for a definitive shipboard study planned for the near future.

In summary, it appears that rapid and efficient reduction of oxygen levels in ballast water both cause substantial mortality of large proportion of transported organisms and minimizes ballast tank corrosion. As such, it may represent a rare example of a solution that simultaneously has benefits for marine conservation and industry.

REFERENCES

- Alanis, I., Berardo, L., De Cristofaro, N., Moina, C., and Valentini, C., 1986. In *Biologically Induced Corrosion*, 102, Houston, National Association Of Corrosion Engineers.
- Andersen, A. B., 2001. Ballast Water Treatment by Ozonation, presented at International Ballast Water Treatment R&D Symposium, IMO London, March 26-27.
- Bibb, M., 1986 In *Biologically Induced Corrosion*, 96, Houston, National Association Of Corrosion Engineers.

- Boyer, H. E. and Gall, T. L., 1985. *Metals Handbook*, American Society for Metals: Metals Park, OH.
- Byers, J., 1999. The distribution of an introduced mollusc and its role in the long-term demise of a native congeneric species. *Biological Invasions*, 1, 339-353.
- Carlton, J. T., and Geller, J. B., 1993. Ecological roulette: The global transport of nonindigenous marine organisms. *Science*, 261, 78-82.
- Cohen, A. N., and Carlton, J. T., 1998. Accelerating invasion rate in a highly invaded estuary. *Science*, 279, 555-558.
- Cooper, W. J., Dinnel, P. A., Gensemer, R. W., Herwig, R. P., Kopp, J. A., Ruiz, G. M., Sonnevil, G., Stubblefield, W. A., and VanderWende, E., 2002. Ozone, Seawater and Aquatic Nonindigenous Species: testing a full-scale ozone ballast water treatment system on an American Oil Tanker. 11th International Conference on Aquatic Invasive Species, Alexandria, VA.
- Daehler, C. C., and Strong, D. R., 1996. Status, prediction and prevention of introduced cordgrass *Spartina* spp. invasions in Pacific estuaries, USA. *Biological Conservation*, 78, 51-58.
- Dias, O. C., and Bromel, M. C., 1990. Material Performance, 29: 53.
- Diaz, R. J., and Rosenberg, R., 1995. Marine benthic hypoxia: a review of its ecological effects and the behavioral responses of benthic macrofauna. *Oceanography and Marine Biology Annual Review*, 33, 245-303.
- Eashwar, M., Subramanian, G., Chandrasekaran, P., and Balakrishnan, K., 1990. In Proc. Corrosion '90, No. 120; Las Vegas, National Association Of Corrosion Engineers.
- Eidsa G. and Risberg, E., 1986. In 'Biologically Induced Corrosion', 109, Houston, National Association Of Corrosion Engineers.
- Fairplay, April 1993. Special Report: Paints and Coatings - Covering the Costs.
- Galil, B. S., and Huelsmann, N., 1997. Protist transport via ballast water - biological classification of ballast tanks by food web interactions. *European Journal of Protistology*, 33, 244-253.
- Grieshaber, M. K., Hardewig, I., Kreutzer, U., and Poertner, H. O., 1994. Physiological and metabolic responses to hypoxia in invertebrates. In: Blaustein, M. P. (Ed.), *Reviews of Physiology Biochemistry and Pharmacology* 125. Springer-Verlag, New York, pp. 43-147.
- Hallegraeff, G. M., 1998. Transport of toxic dinoflagellates via ships' ballast water: Bioeconomic risk assessment and efficacy of possible ballast water management strategies. *Marine Ecology Progress Series*, 168, 297-309.
- Hallegraeff, G. M., and Bolch, C. J., 1991. Transport of toxic dinoflagellate cysts via ships' ballast water. *Marine Pollution Bulletin*, 22, 27-30.
- Hamilton, W. A. and Maxwell, S., 1986. Biological and Corrosion Activities of Sulphate-Reducing Bacteria within Natural Biofilms. *Biologically Induced Corrosion*, Dexter, S. C. ed., National Association of Corrosion Engineers: Houston, TX, pp. 131-136.
- Honeysett, D. G., Van Den Bergh, W. D. and O'Brien, P. F., 1985. *Material Performance*, 24: 34.
- Hardy, J. A. and Bown, J. L., 1984. The Corrosion of Mild Steel by Biogenic Sulfide Films Exposed to Air. *Corrosion*, 40, 650-654.
- Hewitt, C. L., Campbell, M. L., Thresher, R. E., and Martin, R. B., 1999. Marine biological invasions of Port Phillip Bay, Victoria. Centre for Research on Introduced Marine Pests Technical Report Number 20. CSIRO Marine Research, Hobart, 344 pp.
- Hoback, W. W., and Barnhart, M. C., 1996. Lethal limits and sublethal effects of hypoxia on the amphipod *Gammarus pseudolimnaeus*. *Journal of the North*

- American Benthological Society, 15, 117-126.
- Iverson, W. P., 1974. Microbial Iron Metabolism, New York, Academic Press.
- Johnson, L. E., and Carlton, J. T., 1996. Post-establishment spread in large-scale invasions: dispersal mechanisms of the zebra mussel *Dreissena polymorpha*. *Ecology*, 77, 1686-1690.
- Kasahara, K. and Kajiya, F., 1986. In Biologically Induced Corrosion, 171, Houston, National Association Of Corrosion Engineers.
- King, R. A., Skerry, B. S., Moore, D. C. A., Stott, J. F. D. and Dawson, J. L., 1986. In Biologically Induced Corrosion, 83, Houston, National Association Of Corrosion Engineers.
- Lee, W. C., Lewandowski, Z., Okabe, S., Characklis, W. G., and Avci, R., 1993. Corrosion of Mild Steel Underneath Aerobic Biofilms containing Sulfate-Reducing Bacteria Part I: At Low Dissolved Oxygen Concentration. *Biofouling* 7, 197-216.
- Lee, W. C., Lewandowski, Z., Morrison, M., Characklis, W. G., Avci, R., and Nielsen, P. H., 1993. Corrosion of Mild Steel Underneath Aerobic Biofilms containing Sulfate-Reducing Bacteria Part I: At High Dissolved Oxygen Concentration, *Biofouling* 7, 217-239.
- Licina, G. C., 1988. Sourcebook For Microbiologically Influenced Corrosion In Nuclear Power Plants, Palo Alto, Electric Power Research Institute.
- Llanos, R. J., and Diaz, R. J., 1994. Tolerance to low dissolved oxygen by the tubicolous polychaete *Loimia medusa*. *Journal of the Marine Biological Association of the United Kingdom*, 74, 143-148.
- Lutley, W. L. 2001. Treatment for the Mitigation of MIC, In A Practical Manual on Microbiologically Influenced Corrosion, Vol. 2, NACE Press.
- Lutz, R. V., Marcus, N. H., and Chanton, J. P., 1994. Hatching and viability of copepod eggs at two stages of embryological development: anoxic/hypoxic effect. *Marine Biology*, 119, 199-204.
- Marine Engineering Review, January 1991. Life Corrodes Away.
- Matsuda, M., Kobayashi, S., Miyuki, H., and Yoshida, S., 1999. An anticorrosion method for ballast tanks using nitrogen gas. Ship and Ocean Foundation Technical Report.
- McCarthy, S. A., and Khambaty, F. M., 1994. International dissemination of epidemic *Vibrio cholerae* by cargo ship ballast and other nonpotable waters. *Applied and Environmental Microbiology*, 60, 2597-2601.
- Miller, J. D. A. and Tiller, A. K., 1970. In Microbial Aspects Of Metallurgy, 61, New York, Elsevier.
- Mills, E. L., Strayer, D. L., Scheuerell, M. D., and Carlton, J. T., 1996. Exotic species in the Hudson River basin: a history of invasions and introductions. *Estuaries*, 19, 814-823.
- Mountfort, D. O., Hay, C., Dodgshun, T., Buchanan, S., and Gibbs, W., 1999. Oxygen deprivation as a treatment for ships' ballast water: laboratory studies and evaluation. *Journal of Marine Environmental Engineering*, 5 (3).
- Muusse, B., Marcon, J., Van Den Thillart, G., and Almeida-Val, V., 1998. Hypoxia tolerance of Amazon fish: respirometry and energy metabolism of the cichlid *Astronotus ocellatus*. *Comparative Biochemistry and Physiology A*, 120, 151-156.
- National Research Council, 1996. Stemming the tide: controlling introductions of nonindigenous species by ship's ballast water. National Academy Press, Washington, D.C.
- Pacheco, A., Dishinger, T. D. and Tomlin, J. L., 1987. In Proc. Corrosion '87, No. 376, San Francisco, National Association Of Corrosion Engineers.
- Padgett, D. E., Celio, D. A., Hearth, J. H., and Hackney, C. T., 1989. Growth of

- filamentous fungi in a surface-sealed woody substratum buried in salt-marsh sediments. *Estuaries*, 12, 142-144.
- Pierce, R. W., Carlton, J. T., Carlton, D. A., and Geller, J. B., 1997. Ballast water as a vector for tintinnid transport. *Marine Ecology Progress Series*, 149, 295-297.
- Pope, D. H., 1986. A Study Of MIC In Nuclear Power Plants And A Practical Guide For Countermeasures, Final Report Np-4582, Palo Alto, Ca, Electric Power Research Institute.
- Pope, D. H., 1987. Microbial Corrosion In Fossil-Fired Power Plants - A Study Of Microbiologically Influenced Corrosion And A Practical Guide For Its Treatment And Prevention, Palo Alto, Electric Power Research Institute.
- Pope, D. H. and Morris, E. A., 1995. Some Experiences with Microbiologically Influences Corrosion of Pipelines. *Materials Performance*, 34, 23-28.
- Pope, D. H. and Pope, R. M., 2001. Microbiologically Influenced Corrosion in Fire Protection Sprinkler Systems; By: A Practical Manual on Microbiologically Influenced Corrosion, Vol. 2, NACE Press.
- Pope, D. H., Zintel, T. P., Kuruvilla, A. K. and Siebert, O. W., 1988. In *Proc. Corrosion 88*, No. 79, St. Louis, Mo, National Association Of Corrosion Engineers.
- Postgate, J. R., 1979. *The Sulphate Reducing Bacteria*, Cambridge, England, Cambridge University Press.
- Roman, M. R., Gauzens, A. L., Rhinehart, W. K., and White, J. R., 1993. Effects of low oxygen waters on Chesapeake Bay zooplankton. *Limnology and Oceanography*, 38, 1603-1614.
- Ruiz, G. M., Carlton, J. T., Grosholz, E. D., and Hines, A. H., 1997. Global invasions of marine and estuarine habitats by non-indigenous species: mechanisms, extent, and consequences. *American Zoologist*, 37, 621-632.
- Ruiz, G. M., Fofonoff, P., Hines, A. H., and Grosholz, E. D., 1999. Non-indigenous species as stressors in estuarine and marine communities: assessing invasion impacts and interactions. *Limnology and Oceanography*, 44, 950-972.
- Ruiz, G. M., Rawlings, T. K., Dobbs, F. C., Drake, L. A., Mullady, T., Huq, A. and Colwell, R. R., 2000a. Worldwide transfer of microorganisms by ships. *Nature* 408: 49-50.
- Ruiz, G. M., Fofonoff, P., Carlton, J. T., Wonham, M. J., and Hines, A.H., 2000b. Invasions of Coastal Marine Communities in North America: Apparent Patterns, Processes, and Biases. *Ann. Rev. Ecol. Syst.* 31: 481-531.
- Sanders, P. F. and Hamilton, W. A., 1986. In *Biologically Induced Corrosion*, 47, Houston, National Association Of Corrosion Engineers.
- Smith, L. D., Wonham, M. J., McCann, L. D., Ruiz, G. M., Hines, A. H., and Carlton, J. T., 1999. Invasion pressure to a ballast-flooded estuary and an assessment of inoculant survival. *Biological Invasions*, 1, 67-87.
- Stalder, L. C., and Marcus, N. H., 1997. Zooplankton responses to hypoxia: behavioral patterns and survival of three species of calanoid copepods. *Marine Biology*, 127, 599-607.
- Tallqvist, M., Sandberg-Kilpi, E., and Bonsdorff, E., 1999. Juvenile flounder, *Platichthys flesus* (L.), under hypoxia: effects on tolerance, ventilation rate and predation efficiency. *Journal of Experimental Marine Biology and Ecology*, 242, 75-93.
- Tamburri, M.N., Wasson, K., and Matsuda, M., 2002. Ballast water deoxygenation can prevent aquatic introductions while reducing ship corrosion. *Biological Conservation*, 103, 331-341.
- Tatnall, R., Piluso, A., Stoecker, J., Schultz, R. and Kobrin, G., 1981. *Material Performance*, 19: 41.

- Tritton, D. J., 1977. *Physical Fluid Dynamics*. Van Nostrand Reinhold (U.K.) Co., Ltd.
- van den Thillart, G., George, R. Y., and Stromberg, J. O., 1999. Hypoxia sensitivity and respiration of the euphausiid crustacean *Meganyctiphanes norvegica* from Gullmar Fjord, Sweden. *Sarsia*, 84, 105-109.
- Vargo, S. L., and Sastry, A. N., 1977. Acute temperature and low dissolved oxygen tolerances of brachyuran crab (*Cancer irroratus*) larvae. *Marine Biology*, 40, 165-171.
- Vistisen, B., and Vismann, B., 1997. Tolerance to low oxygen and sulfide in *Amphiura filiformis* and *Ophiura albida* (Echinodermata: Ophiuroidea). *Marine Biology*, 128, 241-246.
- Widdows, J., Newell, R. I. E., and Mann, R., 1989. Effects of hypoxia and anoxia on survival, energy metabolism, and feeding of oyster larvae (*Crassostrea virginica*, Gmelin). *Biological Bulletin*, 177, 154-166.
- Williams, R. J., Griffiths, F. B., Van der Wal, E. J., and Kelly, J., 1988. Cargo vessel ballast water as a vector for the transport of non-indigenous marine species. *Estuarine Coastal and Shelf Science*, 26, 409-420.
- Williamson, M., 1996. *Biological Invasions*. Chapman and Hall, London.
- Winters, M. A. and Badelek, P. S. C., 1987. In *Proc. Corrosion 87*, No. 156, San Francisco, National Association Of Corrosion Engineers.
- Wonham, M. J., Carlton, J. T., Ruiz, G. M., and Smith, L. D., 2000. Fish and ships: Relating dispersal frequency to success in biological invasions. *Marine Biology*, 136, 1111-1121.

ACKNOWLEDGMENTS

We would like to thank K. Wasson, M. Matsuda, K. McPherson, and J. Lee for their help with various aspects of this work. The National Oceanic and Atmospheric Administration is funding our current investigations.


Dr. Mario Tamburri is the Principle Investigator of the work presented here. Dr. Tamburri received a B.A. from the University of California at Santa Barbara, a Master's degree from the University of Alabama, and a Ph.D. from the University of South Carolina. After spending six years as a Research Fellow at the Monterey Bay Aquarium Research Institute he has recently joined the faculty at Chesapeake Biological Laboratory, University of Maryland Center for Environmental Science, where he serves as the Chief Scientist of the Alliance for Coastal Technologies. Dr. Tamburri's research interests lie in understanding the mechanisms that regulates basic biological and ecological process and has worked in habitats ranging from estuaries to the deep sea.

Dr. Brenda Little is the Senior Scientist of Marine Molecular Processes at the Naval Research Laboratory (NRL), Stennis Space Center and is leading the investigation of deoxygenation to prevent the corrosion of ballast tanks. Dr. Little received B.S. from Baylor University, a Ph.D. from Tulane University, and has worked extensively on determining the cause of corrosion failures in weapons systems, seawater piping systems, storage tanks and other U.S. Navy equipment.

Dr. Gregory Ruiz of the Smithsonian Environmental Research Center (SERC) received a B.A. from the University of California at Santa Barbara and a Ph.D. from the University of California, Berkeley. Dr. Ruiz is head of SERC's Marine Invasion Research Laboratory that has a staff of approximately 25 biologists and oversees and coordinates the National Ballast Water Information Clearinghouse.

Mr. Peter McNulty obtained a B.S., Industrial Engineering from Lehigh University and is the President of NEI Treatment Systems, Inc. He has 13 years' experience in environmental engineering, systems design, project management, regulatory affairs, business development, and program management. Mr. McNulty is the President of NEI Treatment Systems, Inc., has been leading the efforts to optimize the deoxygenation process through a rapid, in-line oxygen stripping system

*and has developed designs for shipboard
applications of Venturi Oxygen Stripping.*



STEWARDSHIP MEETS 2003

**August 21-22, 2003
Sheraton National Hotel
Arlington, Virginia**

Click Anywhere To Continue



**Session B2
Oil and Ballast Water**

CLICK ON TITLE TO VIEW PAPER

***Experimental Techniques to Determine Oil in Water Concentrations
During Compensated Fuel Ballast Refueling Tests***

Paisan Atsavapranee, Jerry W. Shan, Stephan Verosto

Biodispersion, An Ultimate Solution for Treating Bilge Water

Satya Ganti, Dr. John J. Wille

USS Mississinewa Oil Offloading Operations

Julianna Prevatt, William Walker

Shipboard Biomechanical Oil Water Separator

Richard L. Penny, Dr. Jason A. Caplan, Marika Suominen-Yeh

***Venturi Oxygen Stripping™ as a Ballast Water Treatment to Prevent
Aquatic Invasions and Ship Corrosion***

Dr. Mario N. Tamburri, Dr. Brenda J. Little, Dr. Gregory M. Ruiz, Peter D. McNulty